

debinding and sintering

•Laboratory for Material Process Technology, Institute for Applied Materials - IAM, Karlsruhe Institute of Technology, Germany

** Laboratory for Materials Process Technology, Department of Microsystems Engineering -IMTEK, University of Freiburg, Germany


> *** European Synchrotron Radiation Facility, Grenoble Cedex, France **** Department of Mathematics, TU Kaiserslautern, Germany ***** Fraunhofer Institute for Industrial Mathematics, Kaiserslautern, Germany ¹ oxana.weber@kit.edu


Quantitative Study of Shear Induced Particle Migration during Micro Powder Injection Moulding


O. Weber*,**, 1, A. Rack***, C. Redenbach****, M. Schulz*,**, O. Wirjadi *****

Powder injection moulding provides an opportunity to produce complexly shaped micro components of ceramic or metal. One of the biggest challenges of µ-PIM is to produce non-deforming, dimensionally stable components. Due to the multi-phase character of the feedstock separation effects between powder and binder matrix can occur during the moulding, which have an essential influence on the quality of the green parts and therefore on the dimensional and mechanical properties of the final parts. The main objective of this study is to investigate the effect of the powder particle distribution in injection moulded green micro parts with respect to the moulding parameters using synchrotron-CT and 3D-image evaluation.

Motivation Prevention of inhomogeneous particle distribution Deformation after Flow lines in green parts







Conclusion

The results showed that the variations in the size distribution of the metal powder particles can be detected and give consistent evidence for a monotonic increase in particle size with distance to the injection gate. Current work is focused on consideration of further methods from spatial statistics and of local particle density distributions along flow direction as well as over cross section. See also: J.Mater.Sci.(2011) 46:3568-3573; DOI 10.1007/s10853-011-5270-9

Acknowledgements

The authors would like to acknowledge Elodie Boller (ESRF) for her support at the beamline ID19, the colleagues from KIT for doing the $\mu\text{-PIM}$ experiments and the DFG for funding of the SFB499.





c) separated and individually labeled particles





Distance from injection point [mm]



